



# Black Iron Oxide SS

## Technical Data Sheet

<b>Product Name:</b>	Gelest Black Iron Oxide SS
<b>Product Code:</b>	BIA-SSA
<b>INCI Name:</b>	Iron Oxides, Stearyl Triethoxysilane
<b>CAS #:</b>	1317-61-9, 7399-00-0
<b>EINECS #</b>	215-277-5, 230-995-9
<b>CI Number:</b>	77499

---

### ***TYPICAL PROPERTIES:***

<b><u>Test</u></b>	<b><u>Parameter</u></b>
<b>Appearance:</b>	Black powder
<b>Odor:</b>	Slight, characteristic
<b>Hydrophobicity:</b>	Passes (1 gram floats on 50 ml still deionized water for one hour)
<b>Loss on Drying @105°C three hours:</b>	< 1%
<b>Heavy metals:</b>	
<b>Arsenic:</b>	Maximum 3 ppm
<b>Cadmium:</b>	Maximum 1 ppm
<b>Chromium:</b>	Maximum 100 ppm
<b>Copper:</b>	Maximum 50 ppm
<b>Lead:</b>	Maximum 10 ppm
<b>Mercury:</b>	Maximum 1 ppm
<b>Nickel:</b>	Maximum 200 ppm
<b>Zinc:</b>	Maximum 100 ppm
<b>Microbial content:</b>	< 100 cfu/gram; no pathogens
<b>Composition:</b>	
<b>Black Iron Oxide:</b>	98-99%
<b>Stearyl Triethoxysilane:</b>	1-2%

Note: The values above are typical, not intended for use in preparing specifications.  
Please contact the Gelest PCS sales representative when writing specifications.